

# Technical data sheet

## HPW-103Ag

Cadmium free

### Norm

DIN EN ISO 17672:2017	Ag 155
DIN EN 1044:1999	AG 103
DIN 8513:1979	L-Ag55Sn
EN ISO 3677:2016	B-Ag55ZnCuSn-630/660

### Composition [Mass friction %]

Ag	Cu	Zn	Sn
55	21	22	2

### Valid impurity [max. mass friction%]

Al	Bi	Cd	P	Pb	Si	Ges.
0,001	0,03	0,01	0,008	0,025	0,05	0,15

### Technical specification

Melting range	630-660 °C
Solidus	630 °C
Liquidus	660 °C
Working temperature	660 °C
Density	9,4 g/cm <sup>3</sup>
Tensile strength	400 N/mm <sup>2</sup>
Heat-resisting up to	approx. 200 °C

### Sources of heat

Flame brazing process, Induction heating and Oven soldering

### Application

Steel, Copper and Copper alloy, Nickel und Nickel alloy, Malleable iron

### Delivery forms

Wires	Ø from 0.3 mm to 5.0 mm, available as bunch or on spools
Rods bare	Ø from 1.0 mm to 4.0 mm, in length from 50 mm to 1,000 mm (standard 500 mm)
Rods coated	standard diameter 1.5 mm, 2.0 mm und 3.0 mm; standard length 500 mm (available with different thickness of flux)
Bands	from 0.05 mm thickness, maximum width 70 mm
Preforms	made of wires as rings, sections, or bent components in any shape made of band as discs, shims, blanks, or bent components in any shape
Flux	According to EN 1045 und EN 29454 on request

Other dimensions and forms available on request.